



Roundtower Natural Hydraulic Lime (NHL 5)

Properties

- Roundtower NHL 5 is used in areas of high exposure such as in marine environments, wall copings, lime concrete, etc.
- It allows buildings to "breathe", and does not trap moisture in the walls
- Stone and brickwork that is set in lime is easier to re-use / re-cycle
- Lime re-absorbs a proportion of carbon dioxide (CO₂) emitted during production
- Natural and eco-friendly
- Self healing



Packaging

- 25-kg paper bags. Pallets of 56/49 bags (1400/1225 kg)

Advice

- Always take care in excessive weather conditions (rain, sun and frost) and protect the walls
- Always use the minimum quantity of water necessary to form a workable mix. Excess water may be damaging to the physical characteristics of the mortar
- Work between 8°C and 30°C
- Protect during and after application against low or high temperatures to control setting conditions and avoid any setting issues
- Store bags in dry conditions and off the ground for a maximum of one year after the production date as specified on the bags



Main characteristics

	Unit	Average values*
Physical properties		
Fineness 90 μ	%	5.8
Fineness 200 μ	%	1.00
Expansion	mm	0.5
Bulk density	g/cm ³	0.775
Real density	g/cm ³	2.75
Blaine value	cm ² /g	9642
Mechanical properties		
Setting times	min	312
Compressive strength at 7 days	MPa	3.54
Compressive strength at 28 days	MPa	6.2
Chemical properties		
SO ₃	%	1.48
Free lime content	%	21.9

*Statistical datas, non contractual

Complies with the European Standard for building limes (EN 459-1)

Contact

Roundtower Lime

P : +353 (0) 21 477 6677

P : +44 (0) 1737 581 910

E: info@roundtowerlime.com

Web: www.roundtowerlime.com

